

TRIBRID SEMI FINISHED SINGLE VISION LENS

MATERIAL REFRACTIVE PROPERTY		TRANSMISSION PROPERTY (UNCOAT LENS 2 MM)	
Refractive Index	1.596	Luminous (400-700nm)	90-95%
Abbe Value	41	UV-B (280-315nm)	0.00%
Density	1.23	UV-A (315-380nm)	0.00%

SEMI FINISHED LENS TECHNICAL DATA

NOMINAL BASECURVE	TRUE CURVE		RADIUS		DIA (mm)	CT (mm)	ET (mm)
	FC	BC	FC	BC			
1.00	0.99	8.27	606.06	72.55	75	7.00	16.30
2.50	2.52	8.27	238.10	72.55	75	7.00	14.50
4.00	4.00	8.27	150.00	72.55	75	7.00	12.70
5.00	5.01	8.27	119.76	72.55	75	7.50	11.90
6.00	6.01	8.27	99.83	72.55	75	8.00	11.10
7.00	7.03	8.27	85.35	72.55	75	8.50	10.30
8.00	8.04	8.27	74.63	72.55	75	10.00	10.30
9.00	8.95	8.05	67.04	74.53	70	9.50	8.40
10.00	9.95	7.36	60.30	81.52	65	9.50	6.80
11.00	10.95	7.36	54.79	81.52	65	10.00	6.10